

FILM FACE PLYWOOD

PROMAX



TECHNICAL DATA SHEET



The mark of
responsible forestry




1. MATERIALS DATA

- Core:
 - Eucalyptus, Acacia, or Mixed Hardwood.
 - Legally Source Plantation Wood
- Face/Back:
 - 2 sides High Quality Phenolic Film 135-145 g/m²
- Number of veneer layers:
 - 5–13 plies (depending on thickness).
- Glue:
 - MUF Melamine 25%, 48h Boiling Test
- Reuse times:
 - 15-20 times



2. STANDARD SPECIFICATIONS

- Standard Sizes: 1220 x 2440 mm, 1250 x 2500 mm, as buyer's request.
 - Thickness: 9 mm – 30 mm
 - Moisture Content: ≤ 12%
 - Thickness Tolerance: ±0.5 mm
- Edge Sealing: Water-resistant paint



3. APPLICATIONS

- ✓ Concrete formwork
- ✓ Civil and industrial scaffolding panels
- ✓ Floor casting panels
- ✓ Other applications requiring multiple reuse cycles

4. PHYSICAL & MECHANICAL PROPERTIES

NO.	Parameter	Standard Method	Limit of Quality Standard		Test Result	Unit
1	Bending Strength	TCVN12446:2018	Long Grain	50	61.3	Mpa
			Short Grain	30	42.6	Mpa
2	Modulus of Elasticity (MOE)	TCVN12446:2018	Long Grain	6000	7439	Mpa
			Short Grain	4500	5783	Mpa
3	Bonding Quality	TCVN12447:2018	0.7		0.84	Mpa
4	Moisture	TCVN11905:2017	Max 12		9.8	Mpa

5. PACKING DETAILS

- Sheets per bundle: As per customer requirement
- Packing method: Pallet base or wood blocks, PE wrap, steel strapping
- Label/Logo: Customized upon request



FOMEX GROUP

Headquarter:Fomex Building, No.68/2,Luu
Huu Phuoc Street, Tu Liem Ward, Hanoi,
Vietnam
Website: fomexgroup.vn
Email: qc@fomexgroup.vn
Hotline: +84 877 034 666

